

COTTON VARIETIES DEVELOPED BY THE PCCC (1985 TO 2020) AND THEIR FIBER CHARACTERISTICS

Sr. No.	Variety	Year of Release	Lint % age	Staple length (mm)	Micronaire (ug inch-1)	Strength (tppi/gtex⁻¹)
1	SLH-41	1985	36.0	26.4	4.4	958
2	CIM-70	1986	31.5	29.0	4.2	92.5
3	CIM-109	1990	35.31	27.2	4.4	92.0
4	CIM-240	1992	36.5	27.5	4.7	93.7
5	CRIS-9	1992	34.5	26.5	-	97.0
6	BH-36	1992	38.7	28.0	4.3	100.3
7	CIM-1100	1996	38.0	29.0	3.9	94.0
8	CIM-448	1996	38.0	28.5	4.5	93.8
9	CIM-443	1998	36.7	27.6	4.9	96.0
10	CIM-446	1998	36.2	27.0	4.7	97.4
11	CIM-482	2000	39.2	28.5	4.5	98.0
12	BH-118	2000	38.7	27.6	4.6	96.2
13	Marvi CRIS-5A	2001	35.5	26.8	-	97.5
14	CIM-473	2002	39.7	29.6	4.3	95.2
15	CIM-499	2003	40.2	29.6	4.4	97.3
16	CIM-707	2004	38.1	32.2	4.2	97.5
17	CIM-506	2004	38.5	28.7	4.5	98.9
18	CIM-496	2005	41.1	29.7	4.6	93.5
19	CRIS-134	2004	36.5	27.5	-	97.5
20	CRIS-467	2004	37.0	27.5	4.6	97.2
21	CIM-534	2006	40.1	29.0	4.5	97.2
22	CRIS-121	2006	36.8	27.5	4.9	98.5
23	CIM-554	2009	41.5	28.5	4.7	96.8
24	CRIS-342	2010	38.5	28.4	4.3	95.5
25	CIM-573	2012	39.3	31.6	4.6	90.2
26	Bt CIM-598	2012	41.8	29.0	4.3	94.8
27	BH-167	2012	41.1	29.1	4.7	92.7
28	SLH-317	2012	38.0	29.8	4.4	96.7
29	Bt CIM-595	2013	39.5	29.0	4.7	97.5
30	Bt CIM-599	2013	41.6	28.9	4.6	95.0
31	Bt CIM-602	2013	40.3	29.1	4.2	94.8
32	CIM-608	2013	41.1	28.5	4.6	93.9
33	CRIS-129	2014	38.5	28.5	-	98.5
34	Cyto-124	2016	42.6	30.3	4.4	92.4
35	CIM-620	2016	40.2	28.9	4.6	93.0
36	SLH-8*	2016	39.0	29.0	4.6	-
37	Bt.Cyto-178	2016	40.8	29.0	4.3	105.2
38	Bt CIM-600	2017	40.3	29.0	4.7	94.8
39	Bt Cyto-177	2017	40.0	29.0	4.3	99.9
40	Bt.CIM-179	2017	40.2	28.2	4.2	107.6
41	CIM-598	2017	40.0	29.5	4.6	96.0
42	BT CRIS-508	2017	40.5	28.7	4.7	99.4
43	CRIS-510	2017	39.0	28.2	4.0	92.8
44	CRIS-533	2017	40.5	28.8	4.0	97.8
45	CIM-610	2018	40.2	28.8	4.3	101.9
46	BT.CIM-632	2018	41.6	28.8	4.3	100.4
47	CRIS-585	2020	39.6	28.6	-	31.2
48	CRIS-543	2020	40.5	28.3	-	30.1